

STELLA-CRETE

CRETEPLUS TE

Cement Grout Bonder



- ✓ **Non-Toxic**
- ✓ **Time Saving**
- ✓ **Excellent Bonding Result**
- ✓ **Cost Saving**
- ✓ **Easy Application**
- ✓ **No More Adhesive Cement**
- ✓ **Anti Sagging**
- ✓ **Longer Opening Time**
- ✓ **Enhance Work Efficiency**

Creteplus-TE is a powdered form of additives designed to enhance the adhesion strength and provides more flexibilities of normal cement mortar/grout. **Creteplus-TE** has very high water retention function that prolonged cement curing process that enhances the adhesion strength and provides best workability and high anti-sagging performance. **Creteplus-TE** is odourless, non-toxic and very user friendly.

Product Data Sheet

Packaging	120 gm / bag (100 bags/carton)
Appearance	White
Opening Time	20 mins
Pot Time	75 mins
Toxicity	None
Fire Hazard	Non-flammable
Shelf Life	18 months
Storage	Store in protected area where ambient temperature between 50°F-90°F(10°C-37°C)
Mixing Ratio	25 kg of cement to one bag of Creteplus-TE (120 gm)

Suitable For

Tiling use on all kinds of tile materials; ceramic tiles, porcelain tiles, mosaic tiles and etc.

Tile Surface and Substrate Preparation

- All surface must be clean and free from dust, oil, laitance and all forms of contamination.
- Apply single layer of BA-888 to the rear side of tile, and (or) to the substrate.

Application

- a) Apply cement / grout with Creteplus-TE to floor or wall using a notched trowel or butter laying.
- b) The recommended bed of cement grout with Creteplus-TE should be 3-5mm thick for wall tiling and 5-8mm for floor tiling.
- c) Allow cement grout with Creteplus-TE to set for minimum 7 days before performing pointing gaps grouting.

Grout Mixing Step

- 1) Add in 1 pack (120 gm) of Creteplus-TE into 25 kg of cement (Preferred PCC) dry-mix evenly before pouring it into water.
- 2) Add 7.5-8.5 liters of clean water in the "mixing Container" to receive the pre-mixed cement.
- 3) Pour pre-mixed cement and Creteplus-TE slowly into the "mixing Container". (Optional) Maximum 40% of the fine sand is allowed into mixing.
- 4) Stir evenly until the desired mortar paste is formed.

Recommendation / Remark

- Mixing of the fine sand is recommended if user preferred Ordinary portland cement.



CONTACT US

Stella Crete Sdn Bhd

No 8, Jalan Lira U3/41, Seksyen U3,
40150 Shah Alam, Selangor Darul Ehsan.

Tel: +603 7859 9818 / 012 668 1877
Fax: +603 7859 0188

www.stella-crete.com

enquiries@stella-crete.com

